



### Chrome Magnesite bricks

BRAND	MgO % min	Cr <sub>2</sub> O <sub>3</sub> % min	SiO <sub>2</sub> % max	Fe <sub>2</sub> O <sub>3</sub> % max	CaO % max	A.P. % max	B.D. gm/cc Min	C.C.S. kg/Cm <sup>2</sup> Min.	RUL ta °C min
Chrome Magnesite Bricks									
SR-CMN	35	16	—	—	—	24	2.85	200	1550
SR-CMN R	45	10	—	—	—	22	2.90	350	1600

Remarks: The data relate to standard size pressable bricks. These are subject to variation for bigger pressable and hand moulded shapes. Size tolerance:  $\pm 1.5\%$  or  $\pm 2$  mm whichever is greater.