



MAGNESITE BRICKS

BRAND	MgO % min	Cr ₂ O ₃ % min	SiO ₂ % max	Fe ₂ O ₃ % max	CaO % max	A.P. % max	B.D. Gm/Cc.	C.C.S. Kg/Cm ² min	RUL ta °C min
SR- MGN	82	—	6.5	—	2.5	22	2.60	300	1550
SR-MGD	88	—	5.5	—	2.5	20	2.80	500	1550

Remarks: The data relate to standard size pressable bricks. These are subject to variation for bigger pressable and hand moulded shapes. Size tolerance: $\pm 1.5\%$ or ± 2 mm whichever is greater.