



INSULATING MORTAR, HEAT & AIR SETTING MORTAR

	SR SET 50	SR SET 60	SR SET 70	SR INS M
Physical Properties				
Refractoriness Orton	-	-	-	29
Grain Size (mm)	0-0.5	0-0.5	0-0.5	0-1.0
Service Temp. °C	1550	1600	1650	-
Type of Setting	Air Setting	Air Setting	Air Setting	Ceramic
Chemical Analysis				
Al ₂ O ₃ (%) min.	50	60	70	30
Fe ₂ O ₃ (%) max.	2.5	2.5	3.0	2.0

Tailor made specifications can be made to suit customer's requirement.
Grading: 90% passing through the maximum indicated grain size.