



BASIC MORTARS and RAMMING MASSES

BRAND	MgO % min.	Cr <sub>2</sub> O <sub>3</sub> % min.	SiO <sub>2</sub> % max.	Setting	Grading in mm	Sintering temp. °C	Application temp. °C
Mortar For General Application							
SR MGM	85	-	-	Ceramic	0 - 0.5	1600	
SR MCM	60	15	-	Ceramic	0 - 1	1650	
SR CMM	35	22	-	Ceramic	0 - 1	1650	
Masses For Induction Furnace							
SR RAM IF	75	8	—	Ceramic	0 - 3	800	1750
SR RAM IFB	75	8	—	Ceramic	0 - 5	800	1750
SR RAM-84	84	—	—	Ceramic	0 - 5	1550	1750